

## **TEST REPORT**

LE19 1WD, United Kingdom

Meridian Business Park, Leicester

Centre Court,

Tel: +44 (0) 116 263 0330 Fax: +44 (0) 116 263 0311/12

Web: www.intertek.com/consumergoods

**DATE:** 27<sup>th</sup> January 2012

NUMBER: LECH00327204

**APPLICANT:** Allied International Trading Ltd

t/a Supertouch

Unit A1, Hubert Road

Brentwood Essex CM14 4JE

For the attention of Paul Ansell

SAMPLE DESCRIPTION: White PVC Material

REFERENCE / STYLE NO.: White PVC (43002, 43102)

RETAILER: Supertouch S014

**SAMPLE RECEIVED:** 12<sup>th</sup> January 2012

PURCHASE ORDER: Paul Ansell

**TEST REQUEST:** Plastic Materials and Articles in Contact with Foodstuffs, European Directive

2002/72/EC and amendments (overall migration) (Single Use)

**CONCLUSION:** See comments on page 2.

Tests marked (\*) in this Test Report are not included in the UKAS Accreditation Schedule for this Laboratory Tests marked (^) in this Test Report have been sub-contracted to an agent approved by Intertek Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation



## **TEST REPORT**

Centre Court, Meridian Business Park, Leicester LE19 1WD, United Kingdom

Tel: +44 (0) 116 263 0330 Fax: +44 (0) 116 263 0311/12 Web: www.intertek.com/consumergoods

**NUMBER:** LECH00327204

Specification: Plastic Materials and Articles in Contact with Foodstuffs, European Directive

2002/72/EC

White PVC Material Sample:

**Conclusion:** The overall migration limit for 10mg/dm<sup>2</sup> is specified by the EC Directive 2002/72/EC.

The above samples therefore comply with the overall migration limit for single

exposure to simulant B, C and Milk.

Simulants: B - 3% Acetic Acid

> C – 10% ethanol in water Milk - 50% ethanol in water

Temperature: B, C, Milk - 40°C

**Exposure Time:** 0.5 hours **Exposure Cycle:** Single Use

Testing was carried out by Immersion.

## Results

Sample no.	Description	Average Migration (mg/dm²)	Limit (mg/dm²)
1	Simulant B	3.7	10.0
2	Simulant C	2.6	10.0
3	Milk Simulant	<1.0	10.0

Measured surface area: 1.0 Volume (L): 0.1 Surface area to Volume ratio:

24<sup>th</sup>-26<sup>th</sup> January 2012 Date of Testing:



## **TEST REPORT**

**NUMBER:** LECH00327204

Centre Court, Meridian Business Park, Leicester LE19 1WD, United Kingdom

Tel: +44 (0) 116 263 0330 Fax: +44 (0) 116 263 0311/12 Web: www.intertek.com/consumergoods



**END OF REPORT** 

PAGE 3 OF 3