

## UltraNeo 420

Chemical Product	CAS #	Breakthrough time (minutes)	Permeation level	Standard	Degradation level	Rating
1-Octanol 99%	111-87-5	217	4	ASTM F739	4	++
1,1,1-Trichloroethane 99%	71-55-6	18	1	EN 374-3:2003	1	-
2-Butoxyethanol (Butyl Cellusolve) 99%	111-76-2	100	3	EN 374-3:2003	3	++
2-Nitropropane 99%	79-46-9	26	1	EN 374-3:2003	3	=
2-Propanol (Isopropanol) 99%	67-63-0	286	5	EN 374-3:2003	4	++
Acetic acid 10%	64-19-7	NT	NT		4	NA
Acetic acid 50%	64-19-7	NT	NT		4	NA
Acetic acid 99%	64-19-7	391	5	EN 16523-1:2015	4	++
Acetone 99%	67-64-1	15	1	EN 374-3:2003	4	+
Acetonitrile 99%	75-05-8	11	1	EN 374-3:2003	4	+
Butyl Acetate 99%	123-86-4	22	1	EN 374-3:2003	1	-
Cyclohexane 99%	110-82-7	38	2	EN 374-3:2003	3	+
Dichloromethane (Methylene Chloride) 99%	75-09-2	3	0	EN 374-3:2003	1	-
Diethylamine 98%	109-89-7	7	0	EN 374-3:2003	1	-
Dimethylformamide 99%	68-12-2	42	2	EN 374-3:2003	4	+
Dimethylsulfoxide 99%	67-68-5	360	5	EN 374-3:2003	4	++
Ethanol 95%	64-17-5	130	4	EN 374-3:2003	4	++
Ethyl acetate 99%	141-78-6	12	1	EN 374-3:2003	3	=
Ethylene glycol 99%	107-21-1	NT	NT		4	NA
Formaldehyde 37%	50-00-0	480	6	EN 16523-1:2015	4	++
Hydrochloric acid 10%	7647-01-0	480	6	EN 374-3:2003	4	++
Hydrochloric acid 35%	7647-01-0	480	6	EN 374-3:2003	4	++
Hydrofluoric Acid 40%	7664-39-3	480	6	EN 16523-1:2015	NT	NA
Hydrofluoric Acid 49%	7664-39-3	480	6	EN 374-3:2003	NT	NA
Hydrogen fluoride Anhydrous 99% Gas	7664-39-3	25	1	ASTM F739	NT	NA
Hydrogen peroxide 30%	7722-84-1	480	6	EN 16523-1:2015	NT	NA
Methanol 85%	67-56-1	NT	NT		4	NA

\*not normalized result

### Overall Chemical Protection Rating

Protection rating is determined by taking into account the effects of both permeation and degradation in an attempt to provide users with an overall protection guideline when using our glove products against specific chemicals.

- Used for **high chemical exposure** or chemical immersion, limited to breakthrough time based on a working day.
- Used for **repeated chemical contact**, limited to total chemical exposure i.e. : accumulative breakthrough time based on a working day.
- **Splash protection only**, on chemical exposure the gloves should be discarded and new gloves worn as soon as possible.
- **Not recommended**, these gloves are deemed unsuitable for work with this chemical.

   NT : Not tested

   NA : Not applicable because not fully tested (only degradation OR permeation results)

The chemical test data and overall chemical protection rating should not be used as the absolute basis for glove selection. Actual in-use conditions may vary glove performance from the controlled conditions of laboratory tests. Factors other than chemical contact time

## UltraNeo 420

Chemical Product	CAS #	Breakthrough time (minutes)	Permeation level	Standard	Degradation level	Rating
Methanol 99%	67-56-1	226	4	EN 16523-1:2015	4	++
Methyl Ethyl Ketone (2-Butanone) 99%	78-93-3	9	0	EN 374-3:2003	2	-
Methyl methacrylate 95%	80-62-6	9	0	EN 374-3:2003	2	-
Methylisobutylketone 99%	108-10-1	20	1	EN 374-3:2003	2	=
n-Heptane 99%	142-82-5	33	2	EN 374-3:2003	NT	NA
n-hexane 95%	110-54-3	30	1	ASTM F739	4	+
N-methyl-2-Pyrrolidone 99%	872-50-4	53	2	EN 374-3:2003	3	+
N-N dimethyl acetamide 99%	127-19-5	32	2	ASTM F739	3	+
Naphtha, Hydrotreated Heavy mixture	64742-48-9	113	3	EN 374-3:2003	4	++
Nitric acid 10%	7697-37-2	480	6	EN 374-3:2003	4	++
Nitric acid 20%	7697-37-2	480	6	EN 374-3:2003	4	++
Nitric acid 40%	7697-37-2	480	6	EN 374-3:2003	4	++
Nitric acid 50%	7697-37-2	480	6	EN 374-3:2003	4	++
Nitric acid 65%	7697-37-2	480	6	EN 16523-1:2015	4	++
Nitric acid 68%	7697-37-2	480	6	EN 374-3:2003	4	++
Nitrobenzene 99%	98-95-3	41	2	ASTM F739	2	=
Phosphoric acid 75%	7664-38-2	480	6	EN 374-3:2003	4	++
Sodium hydroxide 20%	1310-73-2	480	6	EN 374-3:2003	4	++
Sodium hydroxide 40%	1310-73-2	480	6	EN 374-3:2003	4	++
Sodium hydroxide 50%	1310-73-2	480	6	EN 374-3:2003	4	++
Styrene 99%	100-42-5	12	1	EN 374-3:2003	1	-
Sulfuric acid 10%	7664-93-9	480	6	EN 374-3:2003	4	++
Sulfuric acid 40%	7664-93-9	480	6	EN 374-3:2003	4	++
Sulfuric acid 50%	7664-93-9	480	6	EN 374-3:2003	4	++
Sulfuric acid 96%	7664-93-9	225	4	EN 374-3:2003	4	++
t-Butyl Methyl Ether 98%	1634-04-4	18	1	EN 374-3:2003	2	=

\*not normalized result

### Overall Chemical Protection Rating

Protection rating is determined by taking into account the effects of both permeation and degradation in an attempt to provide users with an overall protection guideline when using our glove products against specific chemicals.

- Used for **high chemical exposure** or chemical immersion, limited to breakthrough time based on a working day.
- Used for **repeated chemical contact**, limited to total chemical exposure i.e. : accumulative breakthrough time based on a working day.
- **Splash protection only**, on chemical exposure the gloves should be discarded and new gloves worn as soon as possible.
- **Not recommended**, these gloves are deemed unsuitable for work with this chemical.

   NT : Not tested

   NA : Not applicable because not fully tested (only degradation OR permeation results)

The chemical test data and overall chemical protection rating should not be used as the absolute basis for glove selection. Actual in-use conditions may vary glove performance from the controlled conditions of laboratory tests. Factors other than chemical contact time

## UltraNeo 420

Chemical Product	CAS #	Breakthrough time (minutes)	Permeation level	Standard	Degradation level	Rating
Tetrachloroethylene (Perchloroethylene) 99%	127-18-4	11	1	EN 374-3:2003	1	-
Tetrahydrofurane 99%	109-99-9	7	0	EN 374-3:2003	1	-
Toluene 99%	108-88-3	6	0	EN 374-3:2003	1	-
Trichloroethylene 99%	79-01-6	6	0	EN 374-3:2003	1	-
Vinyl acetate 99%	108-05-4	7	0	EN 374-3:2003	2	-
Xylene 99%	1330-20-7	10	0	EN 374-3:2003	1	-

\*not normalized result

### Overall Chemical Protection Rating

Protection rating is determined by taking into account the effects of both permeation and degradation in an attempt to provide users with an overall protection guideline when using our glove products against specific chemicals.

- Used for **high chemical exposure** or chemical immersion, limited to breakthrough time based on a working day.
- Used for **repeated chemical contact**, limited to total chemical exposure i.e. : accumulative breakthrough time based on a working day.
- **Splash protection only**, on chemical exposure the gloves should be discarded and new gloves worn as soon as possible.
- **Not recommended**, these gloves are deemed unsuitable for work with this chemical.

  NT : Not tested

  NA : Not applicable because not fully tested (only degradation OR permeation results)

The chemical test data and overall chemical protection rating should not be used as the absolute basis for glove selection. Actual in-use conditions may vary glove performance from the controlled conditions of laboratory tests. Factors other than chemical contact time